# **Technical Data Sheet**



## **QGel 301**

Fast Cure, High Strength Silicone Gel

### PRODUCT DESCRIPTION

QGel 301 is a clear, very soft, tough, moderately cross-linked silicone polymer. Silicone gels are used to provide protection from vibration, thermal or mechanical shock. Silicone gels also provide excellent moisture protection.

### **KEY FEATURES**

- One to one mix ratio
- Soft, with considerably higher strength than general purpose gels
- Fast 30 minute gel time at room temperature

### **TYPICAL PROPERTIES**

UNCATALYZED			
TEST	QGel 301 A	QGel 301 B	
Appearance	Transparent	Transparent	
Viscosity	1,000 cps	2,000 cps	
Specific Gravity	0.97	0.97	

CATALYZED		
MIX RATIO 1:1		
TEST	RESULT	
Gel Time at 25°C *	20 - 30 minutes	

<sup>\*</sup> Gel time is defined as the time required for the material to become a solid or a semi-solid.

CURED PROPERTIES		
Cure Profile	5 minutes at 150°C	
	10 minutes at 100°C	
	90 minutes at 25°C	
Penetration, 30 minutes at 150°C	5 - 9 mm	

ADDITIONAL PROPERTIES		
Service Temperature Range	-55°C - 204°C	
Adhesion	Excellent adhesion to glass, copper and to select other substrates	
Electrical Properties	Excellent dielectric strength	

1 REV-1

## **Technical Data Sheet**



#### **MIXING**

QGel 301 should be thoroughly mixed using a 1:1 ratio by weight. Once the components are mixed the curing process begins. The gel time of the mixed material is listed above under typical properties. Fast curing gels (less than 30 minute gel time) should be dispensed utilizing automated mix and dispense equipment.

#### **DE-AERATION**

Air trapped during mixing should be removed to eliminate voids in the cured product. Vacuum de-airing may be necessary to completely remove all entrapped air bubbles. To ensure proper deairing, subject the mixed material to 29 inches of mercury.

#### STORAGE AND SHELF LIFE

If QGel 301 A and QGel 301 B are stored in their original unopened containers, in an environment that does not exceed 38°C (100°F) then QSi will warranty the material for a period of 12 months from the date of shipment.

### **DISCLAIMER**

The technical data listed is provided for reference only and is not intended as product specifications. QSi has the capability to customize products as requested. For sales and technical assistance please contact customer service at (804) 271-9010 or 1-800-852-3147.

Please be sure to visit our website daily for our complete product portfolio, new product introductions and more! www.quantumsilicones.com

Quantum Silicones Headquarters 7820 Whitepine Road Richmond, VA 23237

Manufacturing, Research and Development Facility 8021 Reycan Road Richmond, VA 23237

Phone: 804-271-9010 Fax: 804-271-9055 Toll Free: 800-852-3147

2 REV-1