

productinformation

tesa® 62934

800µm double sided PE foam tape

tesa® 62934 is a double sided PE foam tape for constructive mounting applications. It consists of a highly conformable PE foam backing and a tackified acrylic adhesive.

Product benefits:

- Versatile adhesive for high immediate adhesion on numerous substrates
- High ultimate adhesion level for a secure bonding performance
- Fully outdoor suitable: UV, water and ageing resistant
- Compensates for differing thermal expansion of dissimilar materials
- High immediate bonding strength even at low bonding pressure
- Very good cold shock absorbtion

Main Application

- Decorative aluminium cover screens on brown goods
- Doorhandles in kitchen furniture
- Moulded plastic parts
- Mirrors and coloured glass panels

Technical Data

	Backing material	PE foam		Type of adhesive	tackified acrylic
•	Color	black/white	•	Elongation at break	250 %
•	Total thickness	800 μm	•	Tensile strength	8 N/cm

Adhesion to

	Steel (initial) ABS (initial) Aluminium (initial) PC (initial) PE (initial) PET (initial) PP (initial) PS (initial)	17.0 N/cm 17.0 N/cm 17.0 N/cm 15.0 N/cm 2.7 N/cm 12.5 N/cm 2.8 N/cm		Steel (after 14 days) ABS (after 14 days) Aluminium (after 14 days) PC (after 14 days) PE (after 14 days) PET (after 14 days) PP (after 14 days) PS (after 14 days)	17.0 N/cm 17.0 N/cm 17.0 N/cm 17.0 N/cm 2.8 N/cm 17.0 N/cm 5.5 N/cm 17.0 N/cm
:	PVC (initial)	17.0 N/cm		PVC (after 14 days)	17.0 N/cm
:	PET (initial) PP (initial) PS (initial)	12.5 N/cm 2.8 N/cm 15.0 N/cm	:	PE (after 14 days) PET (after 14 days) PP (after 14 days) PS (after 14 days)	2.8 N/cm 17.0 N/cm 5.5 N/cm 17.0 N/cm

For latest information on this product please visit http://l.tesa.com/?ip=62934

tesa°

tesa® 62934

800µm double sided PE foam tape

Properties

Temperature resistance short term	80 °C	 Humidity resistance 	••••
Temperature resistance long term	80 °C	 Softener resistance 	• •
Tack	• • •	 Static shear resistance at 23° 	• • •
Ageing resistance (UV)	• • •	 Static shear resistance at 40° 	•••

Evaluation across relevant tesa® assortment: ••• very good •• good • medium • low

Additional Information

Liner variants:

- PV0 brown glassine paper (71 μm)
- PV10 red transparent PP film (120 μm)
- PV15 blue PE film (100 μm)

Peel Adhesion:

- immediate: foam splitting on Steel, Aluminium, ABS
- after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC

tesa® 62934 has been tested by TÜV Rheinland, Germany. The test confirms the longterm adhesion performance after IEC 61215 / 61646 climate tests and a 85°C temperature resistance. (TÜV report number 21209595).