

SHIN-ETSU

KE3475TUV Conformal Coating

FEATURING:

- 100% Silicone Solids, Medium Viscosity
- Fast, “No-Energy” Room temperature Cure
- Non-Corrosive, Self priming adhesion
- Single Component Chemistry
- UL Recognized Material

Shin-Etsu KE3475TUV is a conformal coating specially processed to offer outstanding insulation performance over a wide range of temperature (-65°C to 200°C). The coating cures quickly upon exposure to atmospheric moisture and exhibits excellent adhesion to most printed circuit board substrates.

TYPICAL PROPERTIES

Before Cure		
	Appearance	Transparent clear to amber
	Viscosity, 25°C, cps	2500
	Specific Gravity, 25°C	.99
	Tack Free Time, min.	5
Cure Type	Moisture	
% Solids	100%	
Physical Properties		
	Hardness, Shore A	25
	Tensile Strength, PSI	115 psi
	Elongation, %	200
	Shear Strength, AL-AL	60 psi

Electrical Properties		
	Volume Resistivity,	3×10^{14} ohm-cm
	Dielectric Strength	22 kV/mm
	Dielectric Constant, 60Hz	3.0 max
	Dissipation Factor, 60Hz	3×10^{-3}
Application Method	Flow Coat Selective Spray Manuel Dip, Brush	
UV Tracer	Yes	

SHELF LIFE

The shelf life for KE3475TUV when stored at 25°C or below is six months from date of shipment. When stored in the original unopened container.

CURE

For optimal properties the recommended cure schedule for KE3475TUV is 3 hours at 25°C and 50% RH in depths of 8 mils or less. The product will become tack free in 5 minutes.

Specifications: *The information and data contained herein are believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since Shin-Etsu Silicones cannot know all of the uses to which its products may be put or the conditions of use, it makes no warranties concerning the fitness or suitability of its products for a particular use or purpose.*

You should thoroughly test any proposed use of our products and independently conclude satisfactory performance in your application. Likewise, if the manner in which our products are used requires governmental approval or clearance, the customer must obtain it.

Shin-Etsu Silicones warrants only that its products will meet its specifications. There is no warranty of merchantability of fitness for use, nor any other expressed or implied warranties. The user's exclusive remedy and Shin-Etsu Silicones' sole liability is limited to refund of the purchase price or replacement of any product shown to be otherwise than as warranted. Shin-Etsu Silicones will not be liable for incidental or consequential damages of any kind.

Suggestions of uses should not be taken as inducements to infringe any patents.