



# Technical Data Sheet

## QGel 300Y High Strength Silicone Gel

### PRODUCT DESCRIPTION

QGel 300Y is a very soft, tough, moderately cross-linked silicone polymer. Silicone gels are used to provide protection from vibration, thermal or mechanical shock. Silicone gels also provide excellent moisture protection.

### KEY FEATURES

- Soft, with considerably higher strength than general purpose gels
- One to one mix ratio
- 24 hour room temperature cure
- Dispensing equipment not necessary

### TYPICAL PROPERTIES

UNCATALYZED		
TEST	QGel 300Y A	QGel300Y B
Appearance	Transparent	Yellow
Viscosity	1,000 cps	2,000 cps
Specific Gravity	0.97	0.97

CATALYZED	
MIX RATIO 1:1	
TEST	RESULT
Gel Time at 25°C *	135 minutes

\* Gel time is defined as the time required for the material to become a solid or a semi-solid.

CURED PROPERTIES	
Cure Profile	30 minutes at 150°C
	60 minutes at 100°C
	20 hours at 25°C
Penetration, 30 minutes at 150°C	5 - 9 mm

ADDITIONAL PROPERTIES	
Service Temperature Range	-55°C - 204°C
Adhesion	Excellent adhesion to glass, copper and to select other substrates
Electrical Properties	Excellent dielectric strength



## Technical Data Sheet

### MIXING

QGel 300Y should be thoroughly mixed using a 1:1 ratio by weight. Once the components are mixed the curing process begins. The gel time of the mixed material is listed above under typical properties. Fast curing gels (less than 30 minute gel time) should be dispensed utilizing automated mix and dispense equipment.

### DE-AERATION

Air trapped during mixing should be removed to eliminate voids in the cured product. Vacuum de-airing may be necessary to completely remove all entrapped air bubbles. To ensure proper de-airing, subject the mixed material to 29 inches of mercury.

### STORAGE AND SHELF LIFE

If QGel 300Y A and QGel 300Y B are stored in their original unopened containers, in an environment that does not exceed 38°C (100°F) then QSi will warranty the material for a period of 12 months from the date of shipment..

### DISCLAIMER

The technical data listed is provided for reference only and is not intended as product specifications. QSi has the capability to customize products as requested. For sales and technical assistance please contact customer service at (804) 271-9010 or 1-800-852-3147.

*Please be sure to visit our website daily for our complete product portfolio, new product introductions and more! [www.quantumsilicones.com](http://www.quantumsilicones.com)*

**Quantum Silicones Headquarters**  
*7820 Whitepine Road*  
*Richmond, VA 23237*

**Manufacturing, Research and Development Facility**  
*8021 Reycan Road*  
*Richmond, VA 23237*

**Phone: 804-271-9010**  
**Fax: 804-271-9055**  
**Toll Free: 800-852-3147**