

productinformation

tesa® 4970

Double-sided filmic tape with high adhesion

tesa® 4970 is a thick white double-sided self-adhesive tape consisting of a PVC-film backing and a tackified acrylic adhesive.

tesa® 4970 features especially:

- Excellent combination of high tack and immediate adhesion
- High coating weight for good bonding performance on rough or dusty surfaces
- Full suitability for longterm applications

Main Application

- Mounting of plastic and wooden trims
- Mounting of decorative POS materials and displays
- Mounting of signs and scales

Technical Data

| • | Backing material | PVC film | Tensile strength | 38 N/cm |
|---|---------------------|-------------------|--------------------|--------------------|
| | Color | white | Type of liner | glassine |
| | Total thickness | 225 μm | Colour of liner | brown |
| | Type of adhesive | tackified acrylic | Thickness of liner | 71 μm |
| | Elongation at break | 20 % | Weight of liner | 82 g/m^2 |

Adhesion to

| • | Steel (initial) | 13.0 N/cm | • | Steel (after 14 days) | 13.6 N/cm |
|---|---------------------|-----------|---|---------------------------|-----------|
| • | ABS (initial) | 13.4 N/cm | | ABS (after 14 days) | 14.4 N/cm |
| • | Aluminium (initial) | 11.5 N/cm | • | Aluminium (after 14 days) | 12.6 N/cm |
| • | PC (initial) | 16.2 N/cm | | PC (after 14 days) | 16.9 N/cm |
| • | PE (initial) | 8.5 N/cm | | PE (after 14 days) | 9.1 N/cm |
| • | PET (initial) | 11.5 N/cm | | PET (after 14 days) | 11.9 N/cm |
| • | PP (initial) | 9.7 N/cm | | PP (after 14 days) | 10.8 N/cm |
| • | PS (initial) | 14.7 N/cm | | PS (after 14 days) | 15.2 N/cm |
| • | PVC (initial) | 12.4 N/cm | • | PVC (after 14 days) | 16.6 N/cm |
| | | | | | |

For latest information on this product please visit http://l.tesa.com/?ip=04970



tesa® 4970

Double-sided filmic tape with high adhesion

Properties

- Temperature resistance short term
- Temperature resistance long term
- Tack
- Ageing resistance (UV)
- Humidity resistance
- Resistance to chemicals
- 60°C
- ••••
- 70 °C Softener resistance
 - Static shear resistance at 23°C
 - Static shear resistance at 40°C



Evaluation across relevant tesa® assortment: •••• very good •• good •• medium • low

Additional Information

A fingerlift version (extended liner), tesa® 7149, is also available.