# productinformation



# tesa<sup>®</sup> ACX<sup>plus</sup> 7054 High Transparency 500 μm double-sided acrylic core tape

tesa<sup>®</sup> ACX<sup>plus</sup> 7054 is a double-sided transparent acrylic core tape. It consists of a high-performance acrylic system and is primarily characterized by its bonding power, stress dissipation and its temperature and weather resistance.

Due to the product's unique formulation, this double-sided acrylic core tape combines very high adhesion levels with the ability to absorb and dissipate high dynamic loads. The viscoelastic, solid acrylic core is able to compensate for thermal elongations of bonded parts.

tesa<sup>®</sup> ACX<sup>plus</sup> 7054 High Transparency is especially suitable for constructive bonding of transparent and translucent materials such as glass or acrylic.

## Main Application

The tesa<sup>®</sup> ACX<sup>plus</sup> product family is suitable for a wide range of constructive bonding applications. To ensure the highest performance possible, our aim is to fully understand the application (including the substrates involved) in order to provide the right product recommendation. Example mounting applications of transparent and translucent materials include but are not limited to:

- Profiles for plissees
- Partition walls (e.g. glass on glass)
- Sign manufacturing (e.g. PMMA on aluminum)

#### Technical Data

:	Backing material Color	solid acrylic transparent	:	Type of adhesive Elongation at break	pure acrylic 1000 %
•	Total thickness	500 µm			

#### Adhesion to

÷	Steel (initial) Aluminium (initial)	11.0 N/cm 9.0 N/cm	;	Steel (after 3 days) Aluminium (after 3 days)	19.0 N/cm 19.0 N/cm
	Glass (initial)	11.0 N/cm		Glass (after 3 days)	17.0 N/cm
	PMMA (initial)	9.0 N/cm		PMMA (after 3 days)	12.0 N/cm

For latest information on this product please visit http://l.tesa.com/?ip=07054

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. They shall be considered as average values and are not appropriate for a specification. Therefore tesa SE can make no warranties, expressed or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. The user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



# tesa<sup>®</sup> ACX<sup>plus</sup> 7054 High Transparency 500 μm double-sided acrylic core tape

Temperature resistance short term	200 °C	Resistance to chemicals	
Temperature resistance long term	100 °C	Softener resistance	• •
Tack	•••	Static shear resistance at 23°C	••••
Ageing resistance (UV)	••••	Static shear resistance at 70°C	•••
Humidity resistance		T-block	•••

## Additional Information

Please note that we recommend using tesa<sup>®</sup> Adhesion Promoter as surface pre-treatment as it leads to a significant improvement of adhesion levels. Which tesa<sup>®</sup> Adhesion Promoter should be used depends on the substrates and the application. We will be glad to advise you in order to find the right solution. For permanent outdoor applications with load-bearing requirements, our first recommendation is our high resistance product within the tesa<sup>®</sup> ACX<sup>plus</sup> family: tesa<sup>®</sup> ACX<sup>plus</sup> 707x High Resistance.

Product variants:

- PV28: Blue film liner
- PV32: White paper liner

Certificates:

- tesa® ACX<sup>plus</sup> 7054 is recognized according to UL Standard 746C. UL File QOQW2.E309290
- tesa® ACX<sup>plus</sup> 7054 is recognized according to UL Standard 879. UL File UYMR2.E479260
- eurolaser certificate: suitable for laser cutting
- Qualified for a credit according to LEED

For latest information on this product please visit <a href="http://l.tesa.com/?ip=07054">http://l.tesa.com/?ip=07054</a>

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. They shall be considered as average values and are not appropriate for a specification. Therefore tesa SE can make no warranties, expressed or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. The user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

