



## CCA800 Series Application Instructions

Chem-Set™

**STONE** NO BLOOM  
REPAIR KITS

**SKU: CCA801, CCA802, CCA851, or CCA852**

**KEEP OUT OF REACH  
OF CHILDREN**

Flammable liquid  
Notice: Vapor may be harmful

### PRECAUTIONS:

- Avoid inhaling
- Use with adequate ventilation
- If swallowed, induce vomiting and contact physician
- Keep away from ignition medium
- Avoid heat, spark, and flame
- See SDS for further information



**BEFORE USING THIS PRODUCT TEST ACTIVATOR IN HIDDEN AREA  
TO MAKE SURE NO DISCOLORATION OCCURS.**

**INSTRUCTIONS FOR USE:** **Note:** It is important to read and understand the following instructions before attempting to use this kit for chip repair to ensure satisfactory results!

1. Be sure the chip to be filled is clean, dry and free from any foreign matter. Use rubbing alcohol to clean the area. Blowout with air if available. Test accelerator on scrap piece of similar stone or inconspicuous area or to ensure no discoloration occurs.
2. Select the desired repair compound for the size hole or crack to be filled. For small holes use the CA5 low viscosity, and for the larger holes select the heavier viscosity CA2400.
3. Use masking to tape to mask off the surrounding area. Carefully fill the hole with small drops of the desired repair compound. Then spray a light mist with the Stone-Tac accelerator and wait a few seconds for the adhesive to cure. Be sure to quickly remove any excess accelerator. The accelerator should not be allowed to dry on the stone. Should the fill not be completely cured, spray with a little more activator. (Do not touch nor attempt to spread the adhesive with your fingers).
4. After the adhesive is cured, use a razor blade, held perpendicular to the surface and carefully level the adhesive with the surrounding area. (If you need to polish, use a buffing pad and polish compound, but be very brief and touch only lightly for a few seconds.)

### IMPORTANT COMMENTS:

**COLORING:** When mixing color it is recommended you add colorant to the heavier CC2400 cyanoacrylate. Also, when mixing colors use only plastic cups or plastic coffee type stirrers. We suggest you mix enough material to fill more than one chip at a time. Follow the same above procedure with the colored adhesive.

**PLEASE NOTE:** Before using this product on a light colored stone or a stone that has been pretreated, test a small piece of scrap to make sure no discoloration occurs. The Stone-tac accelerator is less likely to cause discoloration than other accelerators but this reaction is still possible.

**STORAGE:** Keep bottle tightly closed and open only when using the adhesive. Store at room temperature.

**SAFETY:** \*Cyanoacrylate will instantly bond the skin. Gloves or protective cream is recommended. Should you bond the skin do not attempt to peel the skin apart. Should adhesive get into your eye, seek medical attention immediately.

**If for some reason the test made does not reveal the possible contamination that could occur, there can be a curative by making poultice. The following steps should help:**

1. Obtain some diatomaceous earth or poultice (can be obtained from a pool supply store )
2. Add a solvent such as Acetone or de-natured alcohol to the Diatomaceous earth producing a thick slurry or paste (you may use bleach as well)
3. Apply the poultice to the stain, cover with plastic wrap and let it set or several hours or overnight.
4. Brush dry material away and check to see if the stain is gone. If not repeat steps 1 to 3.

### Additional available products

In the case of emergencies call INFOTRAC 800.535.5053

•Tapes •Custom Packaging •Fluid Dispensing •Specialty Bonding Fasteners •CounterBalance®

The information given and the recommendations made herein are based on our experience and are believed to be accurate. No guarantee as to, or responsibility for, their accuracy can be given or accepted, however, and no statement herein is to be treated as a representation or warranty. In every case we urge and recommend that purchasers, before using any product, make their own tests to determine individual satisfaction and suitability for their particular purposes under their own operating conditions.