

Sikaflex[®]-11 FC

One part advanced polyurethane, elastomeric sealant/adhesive

Description	Sikaflex-11 FC is a one-component, gun-grade, adhesive and sealing compound of permanent elasticity. This dual-purpose material is based on a special moisture-cured polyurethane with an accelerated curing time that meets ASTM C920 Type S, Grade NS, Class 12.5, Use NT, I, M, G, A, O. and Federal Specification TT-S-00230C.
Where to Use	As an elastic adhesive for: <ul style="list-style-type: none">■ Cover plates, gaskets and coverings.■ Acoustic ceiling tiles.■ Floor moldings and door sills.■ Light weight construction materials.■ Wood or metal and door frames.■ Roof tiles. As an elastic joint sealer for: <ul style="list-style-type: none">■ Air ducts and high vacuum systems.■ Containers, tanks, and silos.■ Gaskets in openings in walls or floors for ducts, piling, etc.■ Reservoirs or water retaining structures.■ Aluminum fabrication.■ Bolted lap joints.
Advantages	<ul style="list-style-type: none">■ Excellent adhesion on all cement-based materials, brick, ceramics, glass, metals, wood, epoxy, polyester and acrylic resin.■ Fast cure rate.■ Good weathering and water resistance.■ Non-corrosive.■ Can be painted over with water, oil, and rubber-based paints. (Preliminary tests recommended).■ High durability.
Chemical Resistance	Good resistance to water, weak acids, weak alkalis, sewerage, mineral oils, vegetable oils, fats, fuels. (Not resistant to organic solvents, paint thinner, strong acids, strong alkalis). Consult Technical Service for specific data.
Packaging	Disposable 10.1 fl. oz., moisture-proof composite cartridges, 24/case.

Typical Data (Material and curing conditions @ 73°F and 50% R.H.)

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Shelf Life	12 months in unopened container.
Storage Conditions	Store at 40°-95°F (4°-35°C). Condition material to 65°-75°F before using.
Color	White
VOC Content	28.5 g/L
Application Temperature	40° to 100°F. Sealant should be installed when joint is at mid-range of its anticipated movement.
Service Range	-40° to 170°F
Curing Rate	Tack-free Time (TT-S-00230C) 1 to 2 hours depending on climate. Final Cure 3 to 5 days
Recovery	ASTM C-719 >90%
Shore A Hardness (ASTM D-2240)	40-45
Tensile Properties (ASTM D-412)	
Tensile Stress	225 psi
Elongation at Break	600%
Lap-Shear Strength (ASTM D-1002)	modified, glass substrate
73 F/50% RH	165 psi
Weathering Resistance	Excellent

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://USA.SIKA.COM/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

Construction

 **Sika**[®]

Coverage

10.1 oz Cartridge: Yield in Linear feet				
Depth	1/4"	3/8"	1/2"	
Width	1/4"	24.3		
	3/8"	16.2	10.8	
	1/2"	12.1	8.1	6.1
	3/4"	8.1	5.4	4.0
	1"			3.0
	1.25"			2.4
	1.5"			2.0

How to Use

Surface Preparation	Clean all surfaces. Joint walls must be sound, clean, dry, frost-free, and free of oil and grease. Curing compound residues and any other foreign matter must be thoroughly removed. A roughened surface will also enhance bond.
Priming	Priming is not usually necessary for anodized aluminum, steel, non-absorbent materials such as glass, ceramics, stoneware and tiles. Most substrates only require priming if testing indicates a need or where sealant will be subjected to water immersion after cure. Consult Technical Service at 1-800-933-SIKA for additional information on priming.
Application	Recommended application temperatures: 40°-100°F. For cold weather application, condition material to 65°-75°F before using. Place nozzle of gun into bottom of the joint and fill entire joint. Keep the nozzle in the sealant; continue on with a steady flow of sealant preceding the nozzle to avoid air entrapment. Avoid overlapping of sealant to eliminate entrapment of air.
Tooling and Finishing	Tool as required. Joint dimension should allow for 1/4 inch minimum and 1/2 inch maximum thickness for sealant. Proper design is 2:1 width to depth ratio.
Removal	In case of spills or leaks, wear suitable protective equipment, contain spill, collect with absorbent material, and transfer to suitable container. Ventilate area. Avoid contact. Dispose of in accordance with current, applicable local, state, and federal regulations. In case of emergency, call chemtrec 1-800-424-9300.
Over Painting	Allow 5 day cure at standard conditions when using Sikaflex-11 FC in total water immersion situations and prior to painting.
Limitations	<ul style="list-style-type: none"> ■ Allow 5 day cure at standard conditions when using Sikaflex-11 FC in total water immersion situations and prior to painting. ■ Avoid exposure to high levels of chlorine. (Maximum level is 5ppm). ■ Maximum depth of sealant must not exceed 1/2 in.; minimum depth is 1/4 in. ■ Maximum expansion and contraction should not exceed 12.5% of average joint width. ■ Avoid contact with alcohol and other solvent cleaners during cure. ■ Do not apply when moisture-vapor-transmission condition exists from the substrate as this can cause bubbling within the sealant. ■ Use opened cartridges the same day. ■ When applying sealant, avoid air-entrapment. ■ Since system is moisture-cured, permit sufficient exposure to air. ■ White color tends to yellow slightly when exposed to ultraviolet rays. ■ The ultimate performance of Sikaflex-11 FC depends on proper application, good design and proper preparation of joint surfaces. ■ Not for use in expansion joints. ■ Heavier substrates may require additional support during the cure period. ■ Do not use in contact with bituminous/asphaltic materials.

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

KEEP CONTAINER TIGHTLY CLOSED. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. FOR PROFESSIONAL USE ONLY.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. SALE OF SIKA PRODUCTS ARE SUBJECT SIKA'S TERMS AND CONDITIONS OF SALE AVAILABLE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING 201-933-8800.

Visit our website at usa.sika.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Sika and Sikaflex are registered trademarks. Printed in Canada.

