



Technical Data Sheet

QM 107

7 Shore A, Condensation Cure Moldmaking Material

PRODUCT DESCRIPTION

QM 107 is a two-component, room temperature, condensation cure, silicone material. The cured rubber is very soft, has excellent mechanical properties and good shelf-life stability. This material is used to make large, intricate patterns, skin molds or where extreme flexibility and elasticity are required. A variety of catalysts are offered with this material.

KEY FEATURES

- Low durometer
- Low viscosity
- Fast demold time
- High elongation

Complies with FDA indirect food contact regulation CFR 177.2600, when used with QM Cat Clear FG. Refer to QM Cat Clear FG data sheet for typical properties.

MAIN APPLICATIONS

- Molds for small statues, large statues and monument restoration
- Molds for polyester, polyurethane and epoxy resin castings
- Ideal for pad-printing

TYPICAL PROPERTIES

UNCATALYZED				
TEST	QM 107	QM CAT PURPLE	QM CAT BLUE	QM CAT RED 3
Color	Beige	Purple	Blue	Red
Viscosity	10,000 cps	100 cps	100 cps	100 cps
Specific Gravity	1.22	1.00	1.03	0.95

CATALYZED			
MIX RATIO 10:1 by weight			
PROPERTY	QM CAT PURPLE	QM CAT BLUE	QM CAT RED 3
Color	Light Purple	Light Blue	Light Red
Viscosity	7,500 cps	7,500 cps	7,500 cps
Specific Gravity	1.20	1.20	1.20
Work life at 25°C *	25 minutes	45 minutes	7 minutes
Durometer shore A, 24 hour	6	6	6
Tack-free time	4 - 6 hours	6 - 8 hours	45 - 60 minutes
Demold time	12 - 16 hours	16 - 24 hours	4 - 6 hours

* Work life is defined as the amount of time required for the material to double in catalyzed viscosity.



Technical Data Sheet

CURED PROPERTIES	
3 DAYS @ 25°C	
Durometer, Shore A	7
Tensile Strength	300 psi
Elongation	700 %
Tear B	90 ppi
Linear Shrinkage	< 0.3 %

Thixotropic and styrene resistant specialty catalysts are also available. Please see individual catalyst data sheets for more information.

CURE CHARACTERISTICS

The standard catalyst for the QM 100* series is QM Cat Purple catalyzed 10:1 (base:catalyst) by weight. QM Cat Blue is recommended for those needing a longer working time or those hand mixing larger quantities of QM 107. Faster cure can be obtained using DBT, a higher level of QM Cat Purple, or QM Cat Red 3. However, rapid cure of condensation cure moldmaking rubber often results in a small sacrifice of physical properties or an increase in hardness.

The curing process begins as soon as the catalyst is mixed with the base. The material will cure as described in the data above under normal temperature (25°C) and humidity conditions (50% RH). Because this system is sensitive to heat and humidity, a change in cure speed may be observed if one or both of these variables are altered. A large difference in temperature (+/- 5°C) or humidity (> 60% - 70%) may alter the cure profile of the material. In addition, if the product is to be used with aggressive resins such as high styrene polyester resins, it is recommended that the rubber be allowed to cure for 48 hours.

*QM 100, QM 135 and QM 140 each require their own specific catalyst. Please see individual data sheets for details.

MIXING

All condensation cure catalysts should be thoroughly mixed prior to catalyization.

QSi recommends that the catalyzed material be tested on a small area of the mold prior to use.

QM 107 should be thoroughly mixed with the chosen catalyst using a 10:1 ratio (base:catalyst) by weight. Shake the catalyst well before use. Material should be mixed in a clean, compatible metal or plastic container. The volume of the container should be 3 - 4 times the volume of the material to be mixed. This allows for expansion of the siloxane material during de-aeration.

Mix thoroughly by hand or with mixing equipment while minimizing air entrapment until a homogeneous mixture is obtained.



Technical Data Sheet

DE-AERATION

Air trapped during mixing should be removed by vacuum at 29 inches of mercury. During the process, the material will expand and intermittent evacuation may be required. Typically after releasing the vacuum 2 - 3 times, the mass will collapse on itself at which time the vacuum should be left on for an additional 2 - 4 minute.

STORAGE AND SHELF LIFE

If QM 107 and the chosen catalyst are stored in their original unopened containers, in an environment that does not exceed 38°C (100°F) then QSi will warranty the material for a period of 6 months from the date of shipment.

DISCLAIMER

The technical data listed is provided for reference only and is not intended as product specifications. QSi has the capability to customize products as requested. For sales and technical assistance please contact customer service at (804) 271-9010 or 1-800-852-3147.

*Please be sure to visit our website daily for our complete product portfolio,
new product introductions and more! www.quantumsilicones.com*

Quantum Silicones Headquarters

*7820 Whitepine Road
Richmond, VA 23237*

Manufacturing, Research and Development Facility

*8021 Reycan Road
Richmond, VA 23237*

Phone: 804-271-9010

Fax: 804-271-9055

Toll Free: 800-852-3147