

Chem-Set AW205 HIGH PERFORMANCE CONTACT ADHESIVE OTC STATE COMPLIANT FOR VOC

# TECHNICAL DATA SHEET

Date Prepared : 11/28/2017 Date Revised : 11/28/2017

# **PRODUCT DESCRIPTION:**

**Chem-Set™ AW205** is a high performance contact bond adhesive in a non-flammable solvent. **Chem-Set™ AW205** is suitable for bonding decorative laminate, wood, particleboard, metal, rubber, hardboard, plywood, leather, canvas and many other materials. It is fast drying, oil and waterproof and requires no clamping. Its high tack plus excellent combinability and green strength provides uniform high strength bonds under a wide variety of laminating conditions.

## **ADVANTAGE:**

- High Green Strength
- Aggressive Grab Tack
- High Strength Bonds
- Quick Dry Time
- Good Spray Pattern
- Long Open Time
- Excellent Adhesion to many Substrates
- Excellent for Foam Bonding Applications

### **TYPICAL PROPERTIES:**

Property	Typical Value	
Base:	Compounded Neoprene	
Solvent:	Methylene Chloride*	
Shelf Life:	9 months from Date of Manufacture**	
Color:	Clear/ Red/ Green	
Flash Point:	N/A	
Weight / Gallon	10.74 lbs./ gallon	
VOC Content	71.4 g/L (EPA Method 24)	
Open Time	60 minutes	
Dry Time	2 - 5 minutes	
Solids	15.0 ± 1.5%	
Viscosity	325 - 425 cps	
Coverage	365 ft <sup>2</sup> /gallon @ 2.0 dry grams/ ft <sup>2</sup>	
Formaldehyde	No urea formaldehyde added during adhesive manufacturing	
* Reports have associated repeated and prolonged occupational exposure to solvents with permanent brain and nervous system damage		

\*\* The shelf life for an unopened container of this adhesive stored at

temperatures between 60°F (15.6°C) and 95°F (35°C) is 1 year from date of manufacture. Store out of direct sunlight in a cool, well-ventilated area. Avoid storing container directly on the floor or against an outside wall

APPROVED EQUIPIVIENT.		
Automatic		
	BINKS	DEVILBISS
Spray gun	21,95A	AGX-550
Fluid Tip	63ASS	FX
Fluid Needle	263A, 763A	FX
Air Cap	66SD-3	24
Manual		
	BINKS	DEVILBISS
Spray gun	95, 2100	JGA-510, MSA-510
Fluid Tip	63ASS	FX
Fluid Needle	663A, 563A	FX
Air Can	66SD-3	24

Air Atomization Pressure: 80 – 100 psi Fluid Pressure: 10 – 15 psi Hot spray Temperature: 120°F (93.3°C) maximum

### DIRECTIONS FOR USE:

ADDROVED FOLUDMENT

- Use only after careful consideration of the warnings, directions, and first aid instructions given. Do not thin.
- Surfaces to be bonded should be clean, dry and free of any dust, loose paint, wax, moisture, dirt, grease, oil, rust, or other contaminants.
- Adhesive should be at 60°F (15.6°C) to 95°F (35°C). For best results, adhesive and materials to be bonded should be 60°F (15.6°C) to 95°F (35°C) during application. Allow substrates to acclimate to room temperature for 48 hours before bonding.
- Stir thoroughly before using. Do not thin.
- Apply adhesive uniformly to both surfaces and cover each surface a minimum of 80%. Some porous surfaces may require two coats. 100% coverage is recommended for the edges. Use only approved equipment. For typical applications a coat weight of 2.0 dry grams per square foot is recommended.
- If brushing or rolling adhesive, apply the adhesive with a brush or solvent-resistant medium nap roller.
- Both surfaces must be allowed to dry before bonding. This will usually take from 2 to 5 minutes at room temperature under normal conditions. Heat and humid
- Heat and humidity, or cold weather can cause longer drying times. Surfaces are dry if adhesive is tacky, but no adhesive transfers to the hand when touched.
- Complete the bond within 60 minutes (under normal conditions) after the adhesive is dry. If the two surfaces don't grab immediately when brought into contact, they have dried too long.

- Position coated surfaces carefully before putting them together since no shifting is possible once contact is made.
- Bring surfaces together and immediately apply firm pressure (30 psi) over entire surface working from the center to the edges.
- Let bonded parts cure for at least 72 hours before exposing to direct sunlight of temperatures over 150°F (65.6°C).
- Replace lid after each use and secure tightly for storage.
- Do not use on vinyls or polystyrene foam. Some vinyls contain plasticizers, which can, over time, soften and dissolve the bond, or bleed through/ discolor. When in doubt, or if product is to be used on vinyls, or other light colored materials, conduct compatibility testing on the product to be bonded before use.
- DO NOT use on copper substrates or its alloys. DO NOT use copper spray systems or fluid components.

#### NOTICE TO PURCHASER:

#### WARRANTY:

THIS WARRANTY GIVES YOU SPECIFIC LEGAL RIGHTS, AND YOU MAY ALSO HAVE OTHER RIGHTS, WHICH VARY FROM STATE TO STATE; THEREFORE, SOME OF THE LIMITATIONS STATED ABOVE

MAY NOT APPLY TO YOU. IT IS TO YOUR BENEFIT TO SAVE YOUR DOCUMENTATION UPON PURCHASE OF A PRODUCT. THE INFORMSTION AND SUGGESTIONS FOR USE CONTAINED HEREIN ARE BELIEVED TO BE ACCURATE, BUT ARE NOT TO BE CONSTRUED AS WARRANTIES. USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR HIS OR HER INTENDED USE AND SHALL ASSUME ALL RISK ASSOCIATED THEREWITH.

# **ATTENTION:**

- Empty container remains hazardous until all flammable vapors, which may explode upon ignition, are gone from residue and container. Observe all labeled hazard precautions. Do not cut, puncture, or weld while hazard exists.
- Do not reuse empty container. Recycle, or dispose of, according to all federal, state, and local regulations.
  Follow solvent manufacture's recommendations and instructions for safe handling.

# KEEP OUT OF REACH OF CHILDREN FOR PROFESSIONAL OR INDUSTRIAL USE ONLY USE ONLY WITH APPROVED EQUIPMENT

