## P300 HIGH-TEMP GENERAL PURPOSE CONTACT ADHESIVE













As part of our INDUSTRIAL range, P300 is a web spray adhesive designed for use in applications using the substrates listed.

## PRODUCT DESCRIPTION

TensorGrip P300 is a standard non-flammable solvent contact adhesive with good temperature resistance. Designed to deliver a smooth and strong bond in nearly any application.

#### ADVANTAGES

- Fast, high tack
- Excellent green strength and high heat resistance (over 220°F/105°C)
- Fast drying with long open time
- Excellent high coverage

## DIRECTIONS FOR USE

- TensorGrip P300 is designed as a portable, selfcontained spray system for field or shop applications.
- Apply adhesive to both surfaces to be mated, at 80% to 100% coverage.
- Allow enough time (2-4 minutes or until dry to the touch) for the adhesive to become tacky before bonding.
- Parts should be mated with as much pressure as
- Normal coverage required with web spray pattern is approximately 80%; however, porous surfaces may need a second coat. Initial bond is strong enough to allow cutting or trimming immediately, although ultimate strength is achieved in 1-3 days.
- CCanister system will spray adequately above 60° F. Canister system should be kept in warm area. In the event that the canister gets abnormally chilled, freezes or gives poor or sputtering spray, it should be warmed up before continued usage. Warming canister by immersion in warm water is recommended.
- Notice!!! Do not store at temperatures over 120° F.

#### CANISTER STORAGE/CHANGE OVER

- If you choose to leave the hose and spray gun on the canister, leave the valve on the canister open. Do not disconnect the hose/gun from the canister. Close and lock the spray gun.
- To change or disconnect canister: turn canister valve to the off position, spray out remaining adhesive left in the hose, disconnect the spray hose and gun from the canister.
- Reconnect the spray hose to a new canister of adhesive. OR if you are NOT connecting to a new canister, connect hose to canister of cleaning solvent (sold separately) and spray out until liquid is clear which indicates that the hose and gun is clean.







# P300 HIGH-TEMP DATA SHEET TENSORY TO THE TENSORY THE TENSORY TO THE TENSORY THE TENSORY TO THE TENSORY TO THE TENSORY TO THE TENSORY TO THE T

## CHEMICAL TECHNICAL DATA

### TYPICAL PROPERTIES

Total Solids 22-28%
VOC Content 160.5 g/L
Color Clear or Red

System Flammability Non-Flammable adhesive; Flammable propellant

Solvent System Methylene Chloride

Dry time 3-5 mins dependent on temp & humidity

Open time Lo

Shelf Life
18 months from date of manufacture

#### **PACKAGING**

650ml Aerosol Cans
22L Disposable Canister
108L Returnable Canister
216L Returnable Canister

## STORAGE

#### HANDLING & STORAGE

- Consult Material Safety Data Sheet prior to use.
- Do not store at temperatures over 120°F/50°C.
- · Avoid exposure to direct sunlight.
- Do not store directly on concrete floor.
- Always store above 60°F/15°C
- When connected, keep valve open and hose pressurized at all times
- Always test our adhesives to determine suitability for your particular application prior to use in production



DISCLAIMER OF WARRANTY: Quin Global makes neither warranty of merchantability or fitness for any use nor any other warranty, express or implied, in the sales of its products. Buyer assumes all risk and liability for the results obtained by the use of its products, whether used singly or in combination with other products.



