


P809 CA COMPLIANT CROSSLINKING CONTACT ADHESIVE

DATA SHEET

TensorGrip®



Vinyl



Standard Laminate



FRP/GRP



Metal/Aluminum Sheetting



As part of our **INDUSTRIAL** range, **P809** is a web spray adhesive designed for use on the substrates listed above.

PRODUCT DESCRIPTION

TensorGrip® P809 is a revolutionary high performance, plasticizer resistant adhesive, specially formulated for bonding vinyl, rubber and plastics. Works well on decorative surfaces subject to plasticizer migration as well as many other surfaces including standard laminate and aluminium. Like epoxy, chemically reacts to create permanent bond.

ADVANTAGES

- Bonds vinyl permanently
- Over 300°F (150°C) temperature resistant
- Excellent plasticizer resistance
- Strong, permanent bonds
- High output for fast application
- Resists weathering, water, fuel, oil and many other plasticizers
- Bonds to damp surfaces (moisture cure)
- Semi-repositionable

DIRECTIONS FOR USE

- **TensorGrip® P809** is designed as a portable, self-contained spray system for field or shop applications.
- Apply adhesive to both surfaces to be mated, at 80% to 100% coverage.
- Allow 3-5 minutes or until just slightly sticky, but not longer than 20 minutes before mating substrates.
- Parts should be mated with as much pressure as practical. Ensure 80-100% coverage with spray pattern.
- Within one to two hours, bond is strong enough to allow cutting or trimming, although ultimate strength is achieved in 1-3 days.
- Canister system will spray adequately above 60° F. Canister system should be kept in warm area. In the event that the canister gets abnormally chilled, freezes or gives poor or sputtering spray, it should be warmed up before continued usage. Warming canister by immersion in warm water is recommended.
- Notice!!! Do not store at temperatures over 120° F.

CARE OF SPRAY TIP

Because **TensorGrip®** Crosslinking Contact Adhesives will cure in the tip, if it is going to be more than 10 minutes between uses of the gun:

1. Using **TensorGrip® S800** Point aerosol and gun away from yourself and wear safety glasses
2. Spray whole tip until tip is clean
3. Hold S800 nozzle directly on or within ½" of the orifice of the tip
4. Spray **TensorGrip S800** directly into the orifice until it is clear (1-3 seconds)

CANISTER STORAGE/CHANGE OVER

- If you choose to leave the hose and spray gun on the canister, leave the valve on the canister open. Do not disconnect the hose/gun from the canister. Close and lock the spray gun.
- To change or disconnect canister: turn canister valve to the off position, spray out remaining adhesive left in the hose, disconnect the spray hose and gun from the canister.
- Reconnect the spray hose to a new canister of adhesive. OR if you are NOT connecting to a new canister, connect hose to canister of cleaning solvent (sold separately) and spray out until liquid is clear which indicates that the hose and gun is clean.

QUIN GLOBAL US

5710 F ST, Omaha NE 68117

PH: +1 402 731 3636 | info.us@quin-global.com | www.quiringlobal.com

QUIN
GLOBAL

TensorGrip®

P809 CA COMPLIANT CROSSLINKING CONTACT ADHESIVE

DATA SHEET

Tensorgrip[®]

CHEMICAL TECHNICAL DATA

TYPICAL PROPERTIES

• Total Solids	64-70%
• VOC Content	0 g/L
• Color	Clear
• System Flammability	Flammable Adhesive, Non-Flammable Propellant
• Solvent System	Methyl Acetate
• Dry time	3-5 mins dependent on temp & humidity
• Open time	20 mins
• Handling Strength	1-2 hours
• Full Cure	1-3 days
• Shelf Life	18 months from date of manufacture

PACKAGING

• 7L	Disposable Canister
• 22 L	Disposable Canister

STORAGE

HANDLING & STORAGE

- Consult Material Safety Data Sheet prior to use.
- Do not store at temperatures over 120°F/50°C.
- Avoid exposure to direct sunlight.
- Do not store directly on concrete floor.
- Always store above 60°F/15°C
- When connected, keep valve open and hose pressurized at all times
- Always test our adhesives to determine suitability for your particular application prior to use in production

APPLICATION TOOLS

- Hoses: M150-6 (6'), M150-12 (12'), M150-18 (18')
- Spray Guns: M120 Adj. Spray Gun, M125 18" Wand Adj. Spray Gun
- Spray Tips: 11002B 4" - 18" Medium Build Adj Spray Pattern
- Spray Tip Cleaner: S800-AA



chemical-concepts.com

800.220.1966

410 Pike Road • Huntingdon Valley, PA 19006

DISCLAIMER OF WARRANTY: Quin Global makes neither warranty of merchantability or fitness for any use nor any other warranty, express or implied, in the sales of its products. Buyer assumes all risk and liability for the results obtained by the use of its products, whether used singly or in combination with other products.

QUIN GLOBAL US

5710 F ST, Omaha NE 68117

PH: +1 402 731 3636 | info.us@quin-global.com | www.quiringlobal.com

QUIN
GLOBAL

Tensorgrip[®]

Revision Date 1/2019