Permabond® 3D90 3D Print Infiltrant

ISO 9001:2008 Certified "Our Science ... Your Success"

Introducing Permabond 3D90 cyanoacrylate for strengthening and sealing 3D printed models produced via granular 3D printing methods.

Permabond® 3D90 Features & Benefits

- Ultra-low viscosity and delayed cure speed allows good depth of penetration into parts
- ■Alkoxyethyl formulation is low odour and minimises powdery white residue on surfaces
- Low odour makes it suitable for use in dip baths for large parts
- ■Solvent-free formulation helps minimise workplace hazard
- Adds extra strength and significantly improves printed part performance and durability
- Fills voids and porosities
- ■Moisture cure mechanism no need for measuring and mixing, UV lamp or oven to cure adhesive
- ■Easy to apply either as "on the spot" coating or in a dip bath
- ■Suitable for use on simple or complex, large or small parts
- Clear, colourless appearance
- ■Tack-free finish



Product Data

Appearance	Clear, Colourless
Viscosity @ 25°C	4 mPa.s
Handling Time	10-15 seconds (Steel)
	20-30 seconds (PVC)
	20-30 seconds (Phenolic)
	20-30 seconds (ABS)
Shear Strength	Steel: 16-20 N/mm²
	Aluminium: 8-9 N/mm²
	Zinc: 8 N/mm²
	ABS: >6 N/mm² (SF)
	PVC: 5 N/mm ²
	Polycarbonate: >5 N/mm²
	Phenolic: 4 N/mm²
Impact Strength	3-5 kJ/m²
Hardness	85 Shore D
Dielectric Strength	25 kV/mm
Dielectric Constant	3 @ 1 MHz
Packaging	500g
	2kg
	Bulk 20kg
Storage	2-7°C

SF=Substrate Failure For full technical information, please refer to product data sheet

Distributor Stamp

www.permabond.com

- US Helpline 800-640-7599
- UK 0800 975 9800
- Asia + 86 21 5773 4913
- General Enquiries +44(0)1962 711661
- Deutschland 0800 101 3177
- France 0805 111 388

info.europe@permabond.com info.americas@permabond.com info.asia@permabond.com

