

PRODUCT DATA SHEET

Sikaflex®-296

Direct glazing adhesive for glass windows in the ship building industry

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base	1-component polyurethane
Color (CQP001-1)	Black
Cure mechanism	Moisture-curing
Density (uncured)	1.2 kg/l (10.0 lb/gal)
Non-sag properties	Very good
Application temperature	ambient 10 – 35 °C (50 – 95 °F)
Skin time (CQP019-1)	45 minutes ^A
Open time (CQP526-1)	30 minutes ^A
Curing speed (CQP049-1)	See diagram 1
Shrinkage (CQP014-1)	1 %
Shore A hardness (CQP023-1 / ISO 48-4)	45
Tensile strength (CQP036-1 / ISO 527)	6 MPa (870 psi)
Elongation at break (CQP036-1 / ISO 527)	450 %
Tear propagation resistance (CQP045-1 / ISO 34)	14 N/mm (80 pli)
Tensile lap-shear strength (CQP046-1 / ISO 4587)	4.5 MPa (650 psi)
Insulation resistance (CQP079-2 / DIN IEC 60167)	10 ⁸ Ω cm
Service temperature (CQP509-1 / CQP513-1)	-40 – 90 °C (-40 – 194 °F)
Shelf life	unipack 9 months ^B

CQP = Corporate Quality Procedure

^A) 23 °C (73 °F) / 50 % r. h.^B) storage below 25 °C (77 °F)
DESCRIPTION

Sikaflex®-296 is a high performance elastic gap-filling 1-C polyurethane direct glazing adhesive that cures on exposure to atmospheric moisture. It is suitable for almost all kind of minearal glazing application in the ship building industry.

Sikaflex®-296 meets the regulations set out by the International Maritime Organization (IMO).

PRODUCT BENEFITS

- Resistant to aging and weathering
- Excellent working characteristics
- Solvent- and PVC-free
- Low odor
- Suitable for manual and pump applications
- Black primerless application possible
- Wheelmark approved

AREAS OF APPLICATION

Sikaflex®-296 is designed for direct glazing applications in both the OEM and repair Marine markets. It is suitable for use with all types of mineral glass-based windows used in Marine. Before installing laminated safety glasses, which incorporate heating elements in the PVB sandwich layer, contact Sika's Technical Service Department for advice. Sikaflex®-296 can be tooled to a very fine finish and is suitable for exposed joints.

Seek manufacturer's advice and perform tests on original substrates before using Sikaflex®-296 on materials prone to stress cracking. Sikaflex®-296 is suitable for experienced professional users only. Test with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.



chemical-concepts.com

800.220.1966

410 Pike Road • Huntingdon Valley, PA 19006

PRODUCT DATA SHEET

Sikaflex®-296

Version 03.01 (04 - 2023), en_US
012001212964001000

CURE MECHANISM

Sikaflex®-296 cures by reaction with atmospheric moisture. At low temperatures the water content of the air is generally lower and the curing reaction proceeds somewhat slower (see diagram 1).




Diagram 1: Curing speed Sikaflex®-296

CHEMICAL RESISTANCE

Sikaflex®-296 is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

METHOD OF APPLICATION

Surface Preparation

Surfaces must be clean, dry and free from grease, oil, dust and contaminants.

Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond. Suggestions for surface preparation may be found on the current edition of the appropriate Sika® Pre-treatment Chart. Consider that these suggestions are based on experience and have in any case to be verified by tests on original substrates.

Application

Sikaflex®-296 can be processed at temperatures (climate and product) between 10 °C and 35 °C (50 °C and 95 °F) but changes in reactivity and application properties have to be considered. The optimum temperature for substrate and sealant is between 15 °C and 25 °C (59 °F and 77 °F). Consider the viscosity increase at low temperature. For easy application, condition the adhesive at ambient temperature prior to use.

To ensure a uniform thickness of the bondline it is recommended to apply the adhesive in form of a triangular bead (see figure 1).




Figure 1: Recommended bead configuration

Sikaflex®-296 can be processed with hand, pneumatic or electric driven piston guns. The open time is significantly shorter in hot and humid climate. The glass must always be installed within the open time. Never join bonding parts if the adhesive has built a skin.

Tooling and finishing

Tooling and finishing must be carried out within the skin time of the product. It is recommended using Sika® Slick. Other finishing agents must be tested for suitability and compatibility prior to the use.

Removal

Uncured Sikaflex®-296 can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using a suitable industrial hand cleaner and water.

Do not use solvents on skin!

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- Pre-treatment Chart
For 1-component polyurethanes
- General Guidelines
Bonding and Sealing with 1-component Sikaflex®

PACKAGING INFORMATION

Unipack	600 ml
---------	--------

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LEGAL DISCLAIMER

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by contacting SIKA's Technical Service Department via email at tsmh@us.sika.com. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.** Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling +1 800-933-7452.



chemical-concepts.com

800.220.1966

410 Pike Road • Huntingdon Valley, PA 19006

PRODUCT DATA SHEET

Sikaflex®-296
Version 03.01 (04 - 2023), en_US
012001212964001000

Sika Corporation
30800 Stephenson Highway
Madison Heights, MI 48071
U.S.A.
Telephone: +1 248-577-0020
Email: tsmh@us.sika.com
www.sikausa.com

